



# Krytox™ GPL 226 and GPL 227

## Performance Lubricants

### High-Temperature Anti-Corrosion Greases

## Product Information

Krytox™ GPL 226 and GPL 227 high temperature anti-corrosion greases provide protection from rusting, high temperature corrosion, and antiwear, as well as excellent lubrication over a broad temperature range. Krytox™ GPL 226 and GPL 227 are nonflammable, oxygen-compatible, and chemically inert. Krytox™ lubricants enable extended lubrication intervals and longer equipment life.

Typical applications include corrugator and paper machine bearings, aluminum can manufacturing bearings, vacuum

sputtering machines, welding machines, linear bearings, high temperature fans, clean rooms, chlorine service, textile equipment, tenter frames, high speed motors, instrument bearings, sealed for life motors, conveyor system in glass and aluminum plants, textile calender roll bearings, brick kiln car bearings, CV joints, wheel bearings, universal joints, clutch throwout bearings, paint plant conveyor bearings, ventilation fan bearings, valve lubrication, and starter bearings.

### Product Properties of Krytox™ GPL 226 and GPL 227 Greases

Typical Properties	Krytox™	
NLGI Penetration Grade #2	GPL 226	GPL 227
Penetration Range, mm/10	—	265-295
Estimated Useful Temperature Range, °C (°F)	-36 to 260 (-33 to 500)	-30 to 288 (-22 to 550)
Base Oil Viscosity, cSt		
20 °C (68 °F)	810	1600
40 °C (104 °F)	240	440
100 °C (212 °F)	25	42
Oil Separation, %, 30 hr at 99 °C (210 °F)	3	3
Appearance	White, creamy consistency	White, creamy consistency
Anti-Corrosion Additives	Sodium nitrite	Sodium nitrite
Anti-Rust Rating, ASTM D1743	Pass	Pass
Specific Gravity	1.95	1.95
Four Ball Wear Test, mm, ASTM D2266, 1 hr, 1200 rpm, 107 °C (225 °F), 20 kg load	0.4	0.4
Coefficient of Friction, ASTM D2266	0.11	0.11
Food Contact Approval	NSF H-1	None

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit [krytox.com](http://krytox.com) or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2015 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: H-79776-3 C-10575 (12/15)

